

Recommended Stone Polishes

CMO = Cerium Oxide TO = Tin Oxide LA = Linde A DIA = Diamond CHO = Chromuim Oxide

	CMO	TO	LA	DIA	CHO		CMO	TO	LA	DIA	CHO
ACTINOLITE		X				LABRADORITE		X			X
AGATE	X	X				LAPIS LAZULI		X	X		X
ALABASTER		X				LIMESTONE	X	X	X		X
AMAZONITE		X				LAPIDOLITE					X
AMBER		X				MALACHITE		X	X		X
AMBLYGONITE		X				MOONSTONE		X			
ANDALUSITE		X				NEPHRITE		X	X		X
APATITE			X		X	OBSIDIAN		X			X
AVENTURINE		X				ONYX	X	X			X
AZURITE		X			X	OPAL	X	X			
APOPHYLLITE					X	PERIDOT		X	X	X	
ARAGONITE					X	PETRIFIED WOOD	X	X	X		X
AXINITE	X					PHENACITE		X			
BARITE					X	POLLUCITE	X				
BENITOITE	X					QUARTZ	X	X			
BERYL	X	X		X		RHODOCHROSITE		X	X		X
BLOODSTONE			X			RHODONITE	X		X		X
BRAZILIANITE		X				RUBY				X	
CALCITE		X			X	RUTILE			X		
CASSITERITE		X				SAPPHIRE				X	
CELESTITE					X	SCAPPOLITE	X				
CERUSSITE					X	SCHEELITE					X
CHRYSOBBERYL				X		SERPENTINE		X	X		X
CORAL		X				SMITHSONITE		X			
CORUNDUM				X		SODALITE	X				
DANBURITE		X				SOSOLITE	X				
DATOLITE		X				SPINEL		X	X	X	
DIOPSIDE					X	SHALERITE					X
DIOPTASE	X					SPODUMENE		X			
DIORITE	X	X	X		X	SUNSTONE		X			
ENSTATITE		X				THOMSONITE	X				
EPIDOTE		X				TIGER-EYE	X	X	X		
EUCLASE		X				TITANITE (Sphene)		X			
FELDSPAR	X	X				TOPAZ		X	X	X	
FLUORITE		X			X	TOURMALINE		X	X	X	
GARNET	X	X	X	X	X	TURQUOISE	X	X	X		
GOLDSTONE	X	X				UNAKITE	X				
HEMATITE	X					VARISCITE	X	X	X		
HICKORYITE			X			VESUVIANITE	X				
HOWLITE	X	X	X		X	WILLIAMSITE			X		
HYPERSTHENE		X				WONDERSTONE		X	X		
JADEITE	X	X	X		X	WULFENITE					X
JASPER	X	X	X		X	ZIRCON		X			
KYANITE		X				ZOISITE	X				